



US006093236A

United States Patent [19]

Klabunde et al.

[11] Patent Number: 6,093,236

[45] Date of Patent: Jul. 25, 2000

[54] POROUS PELLET ADSORBENTS
FABRICATED FROM NANOCRYSTALS[75] Inventors: Kenneth J. Klabunde; Olga Koper;
Abbas Khaleel, all of Manhattan, Kans.[73] Assignee: Kansas State University Research
Foundation, Manhattan, Kans.

[21] Appl. No.: 09/093,249

[22] Filed: Jun. 8, 1998

Related U.S. Application Data

[63] Continuation-in-part of application No. 09/087,657, May
30, 1998, abandoned.[51] Int. Cl.⁷ D01D 59/26[52] U.S. Cl. 95/128; 95/133; 95/135;
95/143; 502/400; 502/414; 423/604; 423/605;
423/608; 423/610; 423/622; 423/628; 423/629;
423/632; 423/633; 423/635[58] Field of Search 502/405, 406,
502/407, 415, 324, 325, 328, 329, 331,
335, 336, 338, 337, 340, 343, 345, 350;
264/109, 319, DIG. 25; 423/604, 605, 608,
610, 622, 628, 629, 632, 633, 635

[56] References Cited

U.S. PATENT DOCUMENTS

4,314,932	2/1982	Wakimoto et al.	260/42.53
4,508,841	4/1985	Onuma et al.	502/73
4,543,341	9/1985	Barringer et al.	501/1
4,755,365	7/1988	Funahashi et al.	423/75
5,008,221	4/1991	Ketcham	501/103
5,290,332	3/1994	Chatterjee et al.	65/18.1
5,358,913	10/1994	Chatterjee et al.	501/103
5,420,086	5/1995	Brandau et al.	501/103
5,463,167	10/1995	Ou	585/823

5,540,981	7/1996	Gallagher et al.	428/220
5,670,247	9/1997	Takaoka et al.	428/297
5,712,219	1/1998	Klabunde et al.	502/328
5,759,939	6/1998	Klabunde et al.	502/328
5,807,798	9/1998	Bolt et al.	501/94
5,914,436	6/1999	Klabunde et al.	588/205

OTHER PUBLICATIONS

Ganguly et al.; Sol-Gel Microsphere Pelletization Process
For Fabrication of High-Density ThO₂-2% UO₂ Fuel For
Advanced Pressurized Heavy Water Reactors; *Nuclear Tech-*
nology, vol. 73, pp. 84-94, Apr. 1986.Cano et al.; Development of direct reduction pellets con-
taining MgO by Samarco Mineracao S/A; *Mining Engineer-*
ing, Jun. 1993, pp. 633-636.Browning. Agglomeration: Growing Larger in Applications
and Technology. *Chemical Engineering*. Dec. 4, 1967. pp.
147-169.Agglomeration. *Chemical Engineering*. vol. 58, No. 10, Oct.
1951, pp. 161-170.

Primary Examiner—Tom Dunn

Assistant Examiner—Cam N. Nguyen

Attorney, Agent, or Firm—Hovey, Williams, Timmons &
Collins

[57]

ABSTRACT

Pelletized adsorbent compositions and methods of adsorbing toxic target compounds are provided for the destructive adsorption or chemisorption of toxic or undesired compounds. The pelletized adsorbents are formed by pressing together powder nanocrystalline particles comprising a metal hydroxide or a metal oxide at pressures of from about 50 psi to about 6000 psi to form discrete self-sustaining bodies. The pelletized bodies should retain at least about 25% of the surface area/unit mass and total pore volume of the starting metal particles.

13 Claims, 8 Drawing Sheets

